

Fabrication and strengthening mechanism of crack-free nano-TiC reinforced IN738LC with enhanced mechanical properties by laser powder bed fusion.

SHU, Chang, CHEN, Siyuan, ZHENG, Zhiyu, LU, Xuben, LI, Weining, DE LISI, Michele, BIDARE, Prveen, SHU, Xuedao http://orcid.org/0000-0001-0090-0001-0090-0001-0090-0869

Available from Sheffield Hallam University Research Archive (SHURA) at:

https://shura.shu.ac.uk/32668/

This document is the Published Version [VoR]

Citation:

SHU, Chang, CHEN, Siyuan, ZHENG, Zhiyu, LU, Xuben, LI, Weining, DE LISI, Michele, BIDARE, Prveen, SHU, Xuedao and ESSA, Khamis (2023). Fabrication and strengthening mechanism of crack-free nano-TiC reinforced IN738LC with enhanced mechanical properties by laser powder bed fusion. Journal of Materials Research and Technology, 27, 3835-3848. [Article]

Copyright and re-use policy

See http://shura.shu.ac.uk/information.html

Contents lists available at ScienceDirect



Journal of Materials Research and Technology

journal homepage: www.elsevier.com/locate/jmrt



Fabrication and strengthening mechanism of crack-free nano-TiC reinforced IN738LC with enhanced mechanical properties by laser powder bed fusion

Chang Shu^{a,**}, Siyuan Chen^{b,c}, Zhiyu Zheng^{b,c}, Xuben Lu^{b,c}, Weining Li^a, Michele De Lisi^a, Prveen Bidare^{a,d}, Xuedao Shu^{b,c}, Khamis Essa^{a,*}

^a Department of Mechanical Engineering, University of Birmingham, Birmingham, B15 2TT, UK

^b Faculty of Mechanical Engineering and Mechanics, Ningbo University, Ningbo, 315211, China

^c Zhejiang Key Laboratory of Part Rolling Forming Technology, Ningbo University, Ningbo, 315211, China

^d Department of Engineering and Mathematics, Sheffield Hallam University, Sheffield, S1 1WB, UK

ARTICLE INFO

Keywords: Nanoparticles IN738LC Laser-powder bed fusion Mechanical properties Strengthening mechanism

ABSTRACT

IN738LC alloy has broad application potential in modern aerospace and energy industries due to its excellent high-temperature durability, excellent corrosion and fatigue resistance, however, its application has been greatly limited due to its high crack sensitivity. To address this challenge, this research proposes a method of incorporating TiC nanoparticles to mitigate cracks and enhance the strength of the nickel-based materials. The crack-free TiC-IN738LC materials were successfully fabricated using laser-powder bed fusion. The relationship between the processing parameters and processed quality was studied. The fracture morphology and mechanical properties of samples were analyzed and the strengthening mechanisms of nano-TiC particles were clarified. The results showed that volume energy density (VED) = 111.1J/mm³ is the optimal processing parameter with the laser energy 225W, scanning speed 750 mm/s, and 0.09 mm hatch distance. The effects of processing parameters were discussed in depth. Compared with the virgin IN738LC, the microhardness of TiC-IN738LC is improved by 20 %-40 %, and the tensile strength of TiC-IN738LC. The synergistic effect of fine grain strengthening, load-bearing strengthening and Orowan strengthening mechanisms was accounted for the performance enhancement. The research results provide an experimental reference for selecting the processing parameters of TiC-IN738LC.

1. Introduction

Additive manufacturing (AM) is a transformative manufacturing technology that rapidly developed in the past 30 years. Laser-powder bed fusion (L-PBF) has a high cooling rate (about 10^4 - $10^6 \circ C/s$), and via layer-by-layer deposition and laser-induced non-equilibrium cooling and solidification process, a finer microstructure will be generated [1–4]. Studies have shown that L-PBF is an effective method for fabricating geometrically complex metal components that offer high mechanical performance [1–3,5–7]. Given its promising capabilities, L-PBF has been widely used in numerous applications, including aviation, aerospace, biomedical sensors, and deep-sea explorations [8]. Metal matrix composites are also popular in sectors such as aviation,

aerospace, biomedical sensors, deep-sea explorations, and energy industries, owing to their multi-functional properties. Currently, the production of high-quality composite materials using L-PBF is an area of active research.

Due to the high volume fraction of Ni3(Al,Ti)- γ' , the hard-to-weld nickel superalloy IN738LC boasts a range of exceptional properties, such as high-temperature performance, creep resistance, hot corrosion, and oxidation resistance. IN738LC is a staple in modern aerospace and energy industries [1,9,10]. Using the L-PBF method to produce IN738LC paves the way for its expanded application in diverse sectors. Wang et al. [8] examined the processing parameters of IN738LC in L-PBF and successfully achieved IN738LC with high density, minimal porosity, and a reduced crack rate, thereby establishing the optimal processing

* Corresponding author.

https://doi.org/10.1016/j.jmrt.2023.10.283

Received 15 August 2023; Accepted 26 October 2023 Available online 4 November 2023

^{**} Corresponding author.

E-mail addresses: cxs176@student.bham.ac.uk (C. Shu), k.e.a.essa@bham.ac.uk (K. Essa).

^{2238-7854/© 2023} The Authors. Published by Elsevier B.V. This is an open access article under the CC BY-NC-ND license (http://creativecommons.org/licenses/by-nc-nd/4.0/).

parameter window for IN738LC. Nonetheless, hot cracking remains a significant challenge when working with hard-to-machine nickel superalloys. Identifying strategies to mitigate hot cracking is a primary research objective in the field.

To enhance the γ' precipitation strength of nickel superalloys, incorporating nanoparticles with high modulus and outstanding heat resistance is considered an effective approach to improve their properties and reduce cracking [11–13]. Wang et al. [12] integrated TiC into nickel superalloy GTD222, not only effectively suppressing cracks but also enhancing mechanical properties. Lv et al. [9] improved the mechanical attributes of CM247LC by introducing 1 wt% TiC. The strengthening mechanism imparted by nanoparticles was elucidated through microscopic data analysis. Many studies have illustrated the strengthening mechanism of ceramic particles as reinforcements. The primary strengthening mechanisms encompass Orowan strengthening, fine grain strengthening, load-bearing strengthening, and dislocation strengthening [9,14–16]. However, the elucidation of these mechanisms is mostly based on nickel superalloys such as In718, In625, etc. [16–19]. For the nanoparticles reinforced hard-to-weld nickels, the mechanisms are barely discussed and there are still gaps needed to fill in.

The processing parameters play a critical role in the materials quality [7,20]. For L-PBFed metal materials, prevalent defects, such as pores, cracks, and lack of fusion, detrimentally impact the mechanical properties of the printed sample. Hence, it's crucial to optimize processing parameters to diminish defects and uplift processed quality [7]. The statistical Design of Experiments (DoE) method is currently the main research approach to obtain the relationship between processing parameters and processed quality. Koutiri et al. [21] studied the processing parameters of L-PBFed-IN625 by DoE, and obtained the relationship with the processed quality (surface roughness, porosity rate and tensile strength). The as-printed sample with low porosity and high strength was obtained and provided a valuable processing parameter window as the reference for the future work of L-PBFed-In625. Wang et al. [8] designed L-PBFed IN738LC through full factorials DoE, obtained the relationship diagram of processing parameters, found the correlation between defects and processing parameters, and successfully fabricated the high-density (~99.76 %), crack-free samples. The microstructural results and mechanical tests validated the significant improvement of the properties. Khorasani et al. [5] studied the rheological phenomena of molten pools under different parameters, these results were consistent with the results of density and hardness. By correlating the results of processing parameters and hardness tests as well as the numerical model's validation, the mechanism of molten pool formation and processing parameters were clarified. Zhou et al. [13] successfully printed and strengthened TiC-IN738LC by using L-PBF, but this study only applied one set of processing parameters (laser power 300W, scan speed 1000 mm/s, powder layer thickness 30um, hatch space 90um), the effect on other sets of parameters is not covered. Therefore, although the above research is devoted to the parameter study of Ni-superalloys, there are many blank gaps that have not been studied, especially for the processing parameter analysis of the reinforced difficult-to-machine nickel composite materials.

In this work, the difficult-to-machine nickel superalloy IN738LC was selected as the matrix and the TiC nanoparticles were used as the reinforcements to form TiC-IN738LC metal matrix composite. The processing parameters of TiC-IN738LC by L-PBF were systematically studied. The relationship between processing parameters and the properties including density, porosity, hardness, and tensile strength was revealed. By obtaining the processing parameter network diagram, the optimal parameters of L-PBFed TiC-IN738LC were achieved. Meanwhile, by the analysis of microstructural morphology and mechanical behavior, the strengthening mechanisms and the effect of nano-TiC particles in the L-PBF process were analyzed.

2. Experiments

2.1. Materials

To ensure the high printing quality, spherical shape IN738LC powder (China North Industries Group Corporation Limited, China) was selected in this study, with $d10 = 15.9 \ \mu\text{m}$, $d50 = 34.3 \ \mu\text{m}$ and $d90 = 60.2 \ \mu\text{m}$. The chemical composition of IN738LC is shown in Table 1. Fig. 1a shows the morphology of IN738LC and it shows the powder with the good quality of sphericity. The 50 nm TiC with 99.5 % purity (China North Industries Group Corporation Limited, China) was chosen as the ceramic reinforcement in this work. The morphology of nano-TiC is shown in Fig. 1b. A 4-planetary ball mill machine (QM-QX, Nanjing Nanda Instrument Plant, China) was used to mix the 2 wt% TiC and Nickel superalloy IN738LC. During the ball mill, the Argon gas was filled as the inert gas to prevent the impurity phase that was caused from the oxidation reaction with the powders. To fully disperse and attach the nano-TiC to IN738LC, a set of parameters from ball milling are used: 4:1 ball-to-powder ratio, 200 rpm ball mill speed and 6 h ball mill time. Fig. 1c and (d) show the morphology of TiC-IN738LC after ball milling, and it can be seen that the nano-TiC nanoparticles were evenly distributed to the surface of IN738LC. Fig. 1(e) and (f) displayed the EDS graphs and the presence of both Ti and Ni elements confirms that the TiC nanoparticles were uniformly dispersed around the IN738LC powders before printing.

2.2. L-PBF process and design of experiment

A commercial L-PBF machine (HBD-150D, Shanghai Hanbang United 3D Tech Co., Ltd., China) was used in this work to fabricate the TiC/IN738LC. It is equipped with a 400W IPG fiber laser and a laser spot with a diameter of 70 μ m. Fig. 2 shows the L-PBF schematic diagram, where the cubic samples (8 mm \times 8 mm \times 8 mm) are used for the microstructural observation, and the tensile test specimen adopts the ASTM dimensions and standard [22]. Prior to the printing, the prepared powder was put into a furnace filled with inert gas and dried for 5 h at 40 °C. The L-PBF scanning strategy adopted the 67° rotation in the layer-by-layer scanning direction [9].

A full factorial design with three variables and three levels was used in this work. The three design variables were the laser power (150 W-300 W), scanning speed (500 mm/s-1000 mm/s) and hatch space (0.09 mm-0.12 mm). The layer thickness was set as 0.03 mm for all the trials. Table 2 shows the details of the DoE. For each set of the process parameter, it corresponds to a volume energy density (VED) value, which is generally used as an important reference to correlate the interactions between the laser source and powder [23], namely equation (1):

$$VED = \frac{P}{vhd} \left(J \,/\, mm^3 \right) \tag{1}$$

where P, v, h and d stand for laser power, scanning speed, hatch space and layer thickness, respectively.

2.3. Characterization

Optical microscope (OM) was used to observe porosity as well as the melt pool morphology, and the samples should be well polished before the observations. Scanning electron microscope (SEM) (Hitachi SU5000, Japan) was used to observe the morphology of the fracture and microstructure. Before observation, the samples were ground, mounted, well-polished and etched. The samples were etched for 30 s with the selected etching solution $12mH_3PO_4+48mH_2SO_4+40mHNO_3$ [13]. Electron Back Scatter Diffraction (EBSD) was acquired with 20 kV accelerating voltage and 250 nm step size.

The Archimedes principle was used to measure the density of the as-

Table 1 Chemical composition of IN738LC (wt%).

Ni	Cr	Nb	W	Мо	Та	Ti	Al	Со	С	Sn	Mn	В	Zr
Bal	16	0.8	2.6	1.75	1.7	3.5	3.5	8.5	0.1	0.03	0.03	0.02	0.02



Fig. 1. SEM morphology (a) IN738LC virgin powder, (b) nano-TiC powder, (c) nano-TiC attached to the IN738LC after ball milling, (d) higher magnification of the particle attachment, (e) EDS graph of Ti element and (f) EDS graph of Ni element on the prepared powder.

printed sample ρ_f in this work, with a high-precision (0.001g) weighing scale. The relative density was obtained by the ratio of measured sample density ρ_f to the bulk density ρ_b , where ρ_b is given from the supplier. The images collected by optical microscopy (OM) were used for the porosity and crack analysis. The build direction (BD) of cubic samples was taken as the investigated plane, and each sample collected five different regions on this plane, four of which are at the corners, and one is at the center. ImageJ, an open-source image analysis software, was used to measure porosity rate in this study. The threshold for image processing and adjustment was selected according to Reference [24], where to fix the lower limit on the pores from the segmentation, all the pores with the cubic-voxels smaller than 27 (3 \times 3 \times 3) are automatically neglected.

A Vickers microhardness tester (Wilson VH1102 Micro Hardness Testers, USA) was used for hardness testing in this study. The sample was well-polished to meet the criteria of the microhardness test. Two planes of the sample were used for microhardness testing, which are the building direction (BD) and scanning direction (SD). The sampling points were the straight line on the measured plane and the points were evenly taken with a distance of 0.2 mm. For each point, a 300 N load was





Fig. 2. Schematic diagram of L-PBF process. Dimensional illustration of microstructural samples, tensile samples, and L-PBF as-printed samples.

applied with a dwell time of 10 s. The microhardness tester was calibrated before the test to ensure the accuracy of the result, and the measured systematic error was less than 0.05 %. The final microhardness value was calculated by averaging at least 10 points of data on each measured plane.

A tensile machine (Zwick Amsler 100 HFT, Germany) was used for tensile testing. The tensile tests were performed at a rate of 1 mm/min, and the load direction was perpendicular to the building direction of the sample. For each parameter, three identical samples were used to perform the repeated experiments to ensure the accuracy of the results. The solution heat treatment was performed at 1120 °*C* with accelerated air cooling and 850 °*C* aging for 24 h.

3. Results and discussion

3.1. Density and porosity

Density is a frequently used metric to evaluate L-PBF as-printed samples due to its straightforward examination procedure. Multiple studies have established correlations among density, porosity, and mechanical properties [25]. Because of the inherent variations in material properties, the relationships between density and both microstructure and mechanical performance differ. Therefore, the density insights provided in this study will be valuable for future research on new composite materials.

Fig. 3 illustrates the relationship between VED and density. As

depicted, when the VED is low (40-80 J/mm³), the relative densities range between 80 % and 90 %. For VED values between 80 and 100 J/ mm³, the relative densities notably increase to 96 %–98 %. At a VED of 100–140 J/mm³, the sample density peaks, achieving high-density (>99 %) as-printed samples. However, when the VED exceeds 140 J/ mm³, the sample's density starts to decline, settling between 96 % and 99 %. It's important to highlight that the relative density at higher VED values remains substantially greater than at lower VED values. A lower VED, indicating reduced energy input, can lead to incomplete fusion and unmelted regions. This can result in the development of porous structures and cracks, thereby reducing the sample's density. Conversely, at higher VED values, excessive energy input can impact the molten pool's Marangoni effect. This can trap inert gas in the molten pool, leading to a gas trap effect, which produces fewer pores [26] and reduces relative density. To further optimize the processing parameter window, methodologies like data visualization and correlation quantification can be employed for machine learning [27], offering reliable predictions of the relationship between density and VED. Table 3 shows the results from the DoE table. In this study, the tensile samples were printed with 5 sets of parameters, which the parameters were selected according to the results of density. Overall, the density analysis shows that the VED value of 100–140 J/mm³ is the ideal processing parameter window, and the microstructural analysis in the following will further optimize the processing parameter window.

Lack of fusion (LoF) and keyhole are the two main types of porosity in L-PBFed metal parts. It has been reported that the shape of pores by

Table 2		
Design of experiments	of L-PBFed	TiC-IN738LC

	Layer thickness = 30um							
# Samples	Laser Power (W)	Scanning speed (mm/s)	Hatch space (mm)					
1	150	500	0.090					
2	150	500	0.105					
3	150	500	0.120					
4	150	750	0.090					
5	150	750	0.105					
6	150	750	0.120					
7	150	1000	0.090					
8	150	1000	0.105					
9	150	1000	0.120					
10	225	500	0.090					
11	225	500	0.105					
12	225	500	0.120					
13	225	750	0.090					
14	225	750	0.105					
15	225	750	0.120					
16	225	1000	0.090					
17	225	1000	0.105					
18	225	1000	0.120					
19	300	500	0.090					
20	300	500	0.105					
21	300	500	0.120					
22	300	750	0.090					
23	300	750	0.105					
24	300	750	0.120					
25	300	1000	0.090					
26	300	1000	0.105					
27	300	1000	0.120					

lack of fusion are usually in the irregular shape, with the size ranging from 10 μ m to several millimeters. The lack of fusion can be attributed to insufficient penetration of the upper melt pool into the substrate or previously deposited layers [28]. Fig. 4 shows the porosity graphs under each processing parameter. LoF and keyhole usually exist in samples with lower VED, for example, comparing the porosity with the laser energy of 225 W and 300 W, the laser energy of 150 W with higher

scanning velocity formed more keyholes and unmelted regions, as shown in Fig. 4. With the greater VED, the melting mode of the molten pool changes from the conduction mode to the keyhole mode, resulting in the molten pool forming the deep V shape [29], If the keyhole mode is not carefully controlled, the keyhole will become unstable and repeatedly form and collapse, eventually becoming the deep spherical pores within the sample [30]. As can be seen in Fig. 4, the deep spherical pores were found in samples at high VED.

Fig. 5 shows the relationship between VED and porosity, and the red curve is a third-order polynomial fitting curve, which is used to represent the trend of the data and to predict the data. As evidenced by Figs. 4 and 5, a noteworthy observation can be made in the context of VED ranging between 100 and 120 J/mm³. Within this spectrum, the L-PBFed TiC-IN738LC composite resulted in a considerably low porosity, below 0.3 %, and a lack of cracks. This substantiates the claim that a comprehensive understanding and manipulation of processing parameters can facilitate control over crack inhibition in this innovative composite material. Meanwhile, based on the conclusion drawn from Fig. 3, it agrees with the results in Fig. 5, namely when the VED is within $100-140 \text{ J/mm}^3$, the density is higher and the porosity is lower; when VED is less than 100 J/mm³ or greater than 140 J/mm³, due to the defects such as lack of fusion and keyhole (as shown in Fig. 4), the density is lower and porosity rate is higher. In summary, to achieve the prominent printability (porosity below 0.4 % and crack-free) of L-PBFed samples, the optimal processing window of VED is between 100 J/mm³ and 120 J/mm³.

Fig. 6 shows the relationship between each processing parameter and porosity rate. Fig. 6 is an important reference for determining the effect of specific parameters on porosity rate. The laser power, for instance, has a significant impact on porosity rate, with lower power levels resulting in the formation of keyholes and cracks due to the generation of LoF. Higher laser power inputs, on the other hand, provide more energy to the melt pool dynamics, particularly at lower scanning speeds and smaller hatch distances. This greater energy enables the melt pool to fully melt the powder and produce fewer LoF, resulting in a lower porosity rate. Scanning speed also affects porosity rate, with slower



Fig. 3. Relationship between VED and the relative density of as-printed samples.

Table 3

	DoE	table	with	the	results	of r	elative	density	and	porosity	•
--	-----	-------	------	-----	---------	------	---------	---------	-----	----------	---

Sample #	Laser power (W)	Scan velocity (mm/s)	Hatch space (mm)	VED (J/ mm ³)	Relative density (%)	Porosity (%)
1	150	500	0.090	111.11	96.79	0.15
2	150	500	0.105	95.24	96.05	0.23
3	150	500	0.120	83.33	97.33	0.15
4	150	750	0.090	74.07	99.93	0.32
5	150	750	0.105	63.49	96.33	5.79
6	150	750	0.120	55.56	90.85	6.32
7	150	1000	0.090	55.56	92.18	0.52
8	150	1000	0.105	47.62	85.08	7.09
9	150	1000	0.120	41.67	87.29	7.52
10	225	500	0.090	166.67	97.29	0.42
11	225	500	0.105	142.86	99.86	0.26
12	225	500	0.120	125.00	96.86	1.42
13	225	750	0.090	111.11	99.02	0.17
14	225	750	0.105	95.24	99.05	0.12
15	225	750	0.120	83.33	97.08	3.17
16	225	1000	0.090	83.33	99.01	0.13
17	225	1000	0.105	71.43	92.83	0.19
18	225	1000	0.120	62.50	88.55	0.13
19	300	500	0.090	222.22	96.63	1.90
20	300	500	0.105	190.48	95.77	2.38
21	300	500	0.120	166.67	99.34	0.28
22	300	750	0.090	148.15	99.26	0.15
23	300	750	0.105	126.98	98.87	1.41
24	300	750	0.120	111.11	97.93	0.25
25	300	1000	0.090	111.11	98.79	0.15
26	300	1000	0.105	95.24	99.40	0.36
27	300	1000	0.120	83.33	87.70	0.14

speeds resulting in a higher VED and a longer interaction time between the laser and powder, leading to a lower porosity rate. Conversely, faster scanning speeds reduce the interaction time, resulting in the formation of LoF. Hatch distance, which indicates the density of the neighbouring powder, also affects porosity rate, with shorter distances enabling more complete interaction between the powder and laser, resulting in a lower porosity rate. In summary, the combination of the lowest porosity rate is built under the conditions: the laser power of 225 W, scan velocity of 500 mm/s and hatch space of 0.09 mm.

3.2. Microhardness

A set of 7 groups of parameters were selected for the microhardness experiment based on the density and porosity results, as shown in Table 4. The results of the Vickers hardness test are shown in Fig. 7. For the microhardness in the scan direction, it is obvious to find the maximum value of 625 ± 53 HV is measured at the VED = 111.1 J/mm³, while the minimum value of 468 ± 50 HV is measured at VED = 74.1 J/ mm³. When VED continues to increase (>111.1 J/mm³), the porosity rate gradually increases due to the gas trapping effect, causing the density to decrease, and eventually lowering in the microhardness value. It is worth noting that the microhardness at low VED is much smaller than that at high VED due to the fact that cracks and keyholes are more likely to occur at low VED. For the microhardness in the build direction, the overall hardness value is smaller than that in the scanning direction, and the results follow the similar trend as the scanning direction, namely, $VED = 111.1 \text{ J/mm}^3$ has the largest microhardness and the values are smaller at other VEDs. As shown in Fig. 7, the overall disparity of microhardness in build direction is not as noticeable as the scanning direction. One of the reasons is that the build direction transfers more heat to the substrate or the previous layer, thus it has a more complex thermal cycle history than that in the scanning direction, thus, in building direction, the thermal gradient is larger, causing the greater residual stress and smaller microhardness [31]. According to the previous study, the high density and low porosity will contribute to the enhancement of microhardness [6], the similar conclusion has also been found in this study. In summary, the optimal microhardness was

obtained at VED = 111.1 J/mm^3 with 527 HV in the build direction and 678 HV in the scan direction.

Fig. 8 shows the comparison of microhardness between the TiC-IN738LC and IN738LC. It is obvious that TiC modified IN738LC has greater microhardness than IN738LC in both scanning direction and the building direction. In the scanning direction, the microhardness of TiC-IN738LC is about 35 % higher than that of IN738LC, and about 20 % higher in the building direction. For the L-PBFed IN738LC, the trend follows the similar pattern as the TiC-IN738LC, which it has the highest hardness when $VED = 111.1 \text{ J/mm}^3$ or $VED = 95.2 \text{ J/mm}^3$, its hardness will gradually decrease at other VEDs. For the TiC-IN738LC, due to the higher hardness of nano-ceramic particles TiC, by attaching the nanoparticles TiC to the IN738LC, several strengthening mechanisms will arise during the laser interaction. Since the nanoparticles have greater heat transfer coefficient, it will cause the thermal mismatch effect, along with the Marangoni effect of the molten pool, nanoparticles are easy to nucleate and crystallize on the grain boundary, and the slip movement along the grain boundary becomes difficult, resulting in the inhibition of dislocation, thus, enhancing its strength to resist the deformation, these strengthening mechanisms have been demonstrated and elucidated in previous studies [9,15,26]. It also should be noted that the previous section has shown the good attachment of TiC to IN738LC, the wetting characteristics are ensured, which is essential for printing the high-quality samples. In summary, via the addition of nanoparticles, it will cause thermal mismatch and dislocation effects, thereby the microhardness performance of TiC-IN738LC is reinforced and better than the virgin IN738LC.

3.3. Tensile strength

Fig. 9 shows the results of the tensile test of L-PBFed TiC-IN738LC and IN738LC and the detailed data are given in Table 5. In the tensile test of three groups of TiC-IN738LC, it can be seen that the sample at $VED = 95.2 \text{ J/mm}^2$ has the largest yield stress and ultimate tensile strength, which is 9.7 % and 1.4 % higher than that at VED = 111.1 J/ mm^2 , and 29.7 % and 19.7 % higher than that at VED = 142.8J/mm^2, respectively. When $VED = 111.1 \text{ J/mm}^2$, the elongation rate is higher than the other two groups, which is 45.2 % higher than VED = 95.2J/ mm^2 and 60 % higher than VED = 142.8J/mm². Overall, although the sample at VED = 111.1 J/mm^2 sacrifices slightly in tensile strength, the lower porosity rate, crack-free and better ductility make the VED = 111.1 J/mm² the optimal processing parameter. This work also compared the TiC-IN738LC and IN738LC in tensile tests. The IN738LC in Fig. 9 adopts the optimal parameters determined in the previous research [8], and is fabricated by the same L-PBF machine in this study to ensure the consistency of the data and eliminate the potential errors between the different L-PBF machines. The ductility of IN738LC is much greater than that of TiC-IN738LC, which is 50 %, 72 % and 80 % higher than VED = 111.1 J/mm², VED95.2 J/mm², and VED = 142.8 J/mm², respectively. However, the yield strength and ultimate tensile strength are much smaller than those of the nano-TiC modified IN738LC. This phenomenon widely exists in the ceramic-reinforced metal matrix composites, and the heat treatment is usually to be considered as an approach to improve the elongation [8]. Fig. 10 shows the results obtained in this study compared with the previous studies on hard-to-machine Ni-superalloys [8,32–36]. It should be noted that none of the Nickels were heat treated in Fig. 10. It can be concluded from Fig. 10 that the TiC-IN738LC developed in this study has significantly enhanced mechanical strength and thereby having the considerable potential value to furtherly research.

The microstructural fracture morphology reveals the fracture mechanisms in depth. Fig. 11 compares the difference between brittle fracture and ductile fracture and shows clear dissimilarity of brittle and ductile fractures in the microstructures. On the surface of the brittle fracture, there are lumpy blocks, which are in the shape of regular strips. Meanwhile, the long grooves and large protrusions on the surface will



Fig. 4. Results of porosity rate under each processing parameter for all 27 L-PBFed as-printed samples. All the pictures have the same scale bar (100 µm).



Fig. 5. Relationship between VED and porosity rate of as-printed samples.

significantly reduce the tensile strength. These coarse blocks and strips are less congregated than dimples (Fig. 11a, b, c) and it is easier to cause the defects and undermine ductile properties. On the other hand, there are many dimples on the ductile fracture (Fig. 11d). The deformation of the dimples can improve the plasticity of the material [37,38]. When VED = 95.2 J/mm³, the ductility of the material decreases significantly, as there are many unmelted particles and irregular blocks, which will eventually become the source of cracks and lead to the brittle fractures (Fig. 11a). In comparison, when VED = 142.8 J/mm³, the fracture still

has the apparent characteristics of brittle fracture, however, due to the high energy input, there is no unmelted particle found (Fig. 11c). When $VED = 111.1 \text{ J/mm}^3$, there are some dimples arisen (Fig. 11b) and the ductile property is improved as shown in Fig. 9. However, when comparing the fracture morphology with the IN738LC, the IN738LC has much denser dimples than TiC-IN738LC (Fig. 11d) and thereby a better ductility as presented in Fig. 9. Previous studies have clarified that the ductile fracture initiates from the fracture source and rapidly propagates to the final fracture zone, however, when the protruding cracks encounter the internal micro-pores or unmelted powder, they will stop extending and lead to a clear boundary on the fracture morphology. The fibre stripes are unevenly distributed at the edge of the fracture and prone to generate the large stress concentration region, eventually leading to the ductile fracture [39]. The dimples are beneficial to the ductility but when the excessive dimples happen, it is prone to generate a larger stress concentration area and causing the strength in the tensile direction is impaired. As discussed above, the evidence of the fracture morphology agrees with the tensile test results.

3.4. The strengthening mechanisms of nano-TiC particles

The anisotropic nature of materials by the L-PBF process is often reflected by the grain shape and size. Fig. 12 shows the EBSD data of the IN738LC and TiC-IN738LC. As visible in Fig. 12a, L-PBFed IN738LC alloy is characterized by elongated grains. An example of a completely different grain structure is shown in Fig. 12b: the alloy containing some TiC nanoparticles is indeed characterized by a fine distribution of the columnar grains, by impeding the grain boundary growth and forming the new nucleate sites. Fig. 12c and d show the grain size of pure IN738LC and TiC-IN738LC, and with the addition of the nano-TiC, the



Fig. 6. The relationship between porosity rate and each processing parameter.

Table 4			
The details	of L-PBFed	microhardness	samples.

Sample #	Laser power (W)	Scan velocity (mm/ s)	Hatch space (mm)	VED (J/ mm ³)	Density (%)	Porosity (%)	BD Microhardness (HV)	SD Microhardness (HV)
1	150	750	0.090	74.1	98.93	0.32	497.6	468.0
2	225	500	0.105	142.9	99.86	0.26	502.2	562.7
3	225	750	0.090	111.1	99.02	0.17	514.2	625.8
4	225	750	0.120	83.3	97.08	3.17	511.2	515.0
5	300	500	0.120	166.7	99.34	0.28	493.3	506.0
6	300	1000	0.105	95.2	99.40	0.36	508.9	541.9
7	300	750	0.105	127.0	98.87	1.41	487.2	598.5



Fig. 7. Microhardness results in the build directions and scan direction.

grain size is fully refined and much smaller than the pure IN738LC [40]. These nanoparticles prevent grain overgrowth and interfere with recrystallization. The occurrence of recrystallization is related to the accumulated internal strain energy. This energy exists in the form of dislocation density. Without recrystallization, large dendrites would remain and reduce mechanical properties [41].

According to the Hall-Petch formula, smaller grain sizes result in higher yield strengths [42]. The formula states that the yield strength of a polycrystalline material is inversely proportional to the square root of its grain size. Mathematically, the Hall-Petch formula can be expressed as:

$$\sigma_y = \sigma_0 + k_y d^{-\frac{1}{2}} \tag{2}$$

where σ_y is the yield strength of the material, σ_0 is the intrinsic strength of material, k_y is a constant term called the Hall-Petch slope and d is the average grain size of the material. According to the literature [43], the grain size strengthening $\Delta \sigma_y$ can be solved, with the lower limit 88 MPa to the upper limit 187 MPa, where in present work, the $\Delta \sigma_y$ is around 200 MPa and it slightly higher than the Hall-Petch method. Overall, the smaller grain size explains why the tensile strength is improved by the addition of the nano-TiC particles.

Fig. 13 shows the schematics of nano-TiC reinforced IN738LC





Fig. 9. Tensile test results of TiC-IN738LC under different VED.

mechanism. When IN738LC powders are heated to high temperatures, the nanoparticles within them can impede the columnar growth and rearrange IN738LC matrix to form the smaller grains. One of the reasons is that nanoparticles can act as pinning sites for grain boundaries. Grain boundaries are the regions between individual grains, and they can be areas of high energy. When the IN738LC powders is heated, atoms can diffuse across grain boundaries and cause the grains to grow. However, if there are nano particles in the material, they can act as obstacles to this diffusion and grain boundary migration process, impeding grain growth [44]. Also, due to size of nano particles, they are typically much smaller than the grains themselves. When a material is heated, the larger grains will tend to grow at the expense of the smaller ones driven by interface

Table 5The results of the tensile test.

Description	Yield Strength (MPa)	Ultimate Tensile Strength (MPa)	Elongation (%)
TiC–In738LC VED = 111.1	1110 ± 21	1518 ± 12	2.1 ± 0.05
TiC–In738LC VED = 95.2	1230 ± 33	1541 ± 23	1.15 ± 0.04
TiC-In738LC VED = 142.8	1141 ± 15	1321 ± 16	$\textbf{0.84} \pm \textbf{0.02}$
$\begin{array}{l} \text{In738LC} \\ \text{VED} = 105.2 \end{array}$	864 ± 24	1238 ± 45	$\textbf{4.2}\pm\textbf{0.10}$



Fig. 8. Microhardness comparisons between the TiC-IN738LC and IN738LC in different directions.



Fig. 10. Comparison of elongation rate and ultimate tensile strength between this study (circled in the graph) and other difficult-to-machine nickel superalloys studies.

energy. However, if there are nano particles present, they can act as nucleation sites for new grains, which can compete with the existing larger grains for material. This competition can impede the growth of the larger grains, leading to a finer microstructure [45].

Fig. 14 illustrates the microstructure of TiC-IN738LC, clearly depicting the presence of the γ' phase and the smaller secondary γ' precipitates. This observation substantiates the hypothesis that the

introduction of nano-TiC nanoparticles does not obstruct the γ' phase generation, but rather augments its proliferation. The load-bearing strengthening mechanism is typically relevant to coherent precipitates, such as primary and secondary gamma prime (γ') phases, often observed in nickel-based superalloys [46]. The significant contribution of these γ' phases to the tensile strength of the material should be recognized. When subjected to external stress, the load distribution is facilitated between the material matrix and the precipitates. Owing to their intrinsic strength and stability, the precipitates effectively enhance the overall material strength by bearing a portion of the applied load. Essentially, these precipitates function as reinforcing elements within the matrix. The smaller secondary γ' precipitates play a pivotal role not only in load distribution but also in obstructing dislocation movement. The introduction of these precipitates increases the obstacle density that dislocations have to circumnavigate, resulting in additional strengthening. This process elevates the yield strength, which is instrumental in improving the overall tensile strength of the material.

In Fig. 15, EDS analysis was examined specifically in the grain boundary region. The analysis indicates a high concentration of Ti elements within this area, suggesting that the incorporation of TiC nanoparticles tends to accumulate at the grain boundary and the TiC nanoparticles function as impediments to dislocation movement. The EBSD result validates this observation, highlighting that the addition of these nanoparticles results in a significantly reduced average grain size compared to pure IN738LC. This phenomenon aligns with the Orowan strengthening mechanism, which posits that the creation of a dislocation loop around a nanoparticle demands more energy than navigating through an unobstructed lattice [47]. Consequently, the introduction of TiC nanoparticles increases the energy threshold required for the plastic



Fig. 11. Fracture morphologies under different processing parameters. (a) TiC-IN738LC with VED = 95.2 J/mm^3 with magnified region inside; (b) TiC-IN738LC with VED = 111.1 J/mm^3 ; (c) TiC-IN738LC with VED = 142.8 J/mm^3 ; and d) IN738LC.







Fig. 12. EBSD results of IN738LC and TiC-IN738LC composite: (a) IPF of IN738LC; (b) IPF of TiC modified IN738LC; (c) Grain size distribution graphs of pure IN738LC; (d) Grain size distribution graphs of TiC-IN738LC.

deformation of the material. This increased energy requirement, in turn, amplifies the material's yield strength and hardness.

According to the experimental data, the processing parameters, which define the VED, correlate with the microhardness and tensile strength. From Figs. 3 and 7, at high scanning speeds, the obtained density and hardness are lower, which may be related to wettability and Rayleigh instability. The temperature of molten pool is calculated using Equation (3) below [48]:

$$Tmp = \frac{C_2}{\lambda \ln\left(\frac{C_1 S_2 H_S}{L_P \lambda^2} + 1\right)}$$
(3)

where C1 and C2 are the Planck's distribution constants, λ is the wavelength of the laser. Scanning speed is inversely proportional to melt pool temperature, and a higher scanning speed leads to a lower temperature and higher surface tension (according to the thermocapillary effect) [30,31]:

$$\gamma = \gamma^* \left(\frac{T_C - T_0}{T_C} \right) \left[1 - \left[\frac{c_2}{(T_c - T_0)\lambda ln \left(\frac{c_1 s_c H_c}{L_p \lambda^2} + 1 \right)} - \frac{T_C - T_0}{T_C} \right] \right]^n$$
(4)

For Equation (4), γ^* is constant for each liquid, *Tc* is the critical temperature and T_0 is the reference temperature. Therefore, based on Equation (5), the surface tension values of the solid-liquid and liquid-gas phases are larger, increasing the chance of droplet generation [48–50]. This phenomenon will lead to low wettability and an increasing chance of spheroidization, which is a common defect in metal AM and causes the porosity rate to increase and decrease the density and hardness [5, 48].

$$S = \gamma_{SG} - (\gamma_{SL} + \gamma_{LG});$$

If S> 0Filmappears (5)



Fig. 13. Schematic of nano-TiC reinforced IN738LC strengthening mechanism. The columnar dendrites are not shown on all the grains for the simplification.



Fig. 14. The microstructure of TiC-IN738LC. The primary γ' phase (cuboidal) and secondary γ' phase (spherical).



Fig. 15. SEM/EDS of the TiC-IN738LC at the grain boundary region.

If S< 0Dropletappears;

Figs. 3 and 7 show that lower hardness and density were obtained with the lower input of laser power. According to Equation (3), less energy is transmitted to the molten pool at the lower laser power and the

temperature of the molten pool is therefore decreased. In this case, due to the lack of the Marangoni convection, causing the higher heat penetration and generating more steam and bubbles within the molten pool. The bubbles tend to escape from the molten pool, and the interaction of steam forces with the hydrostatic pressure and surface tension will result

Journal of Materials Research and Technology 27 (2023) 3835-3848

in the formation of small pores and eventually weaken hardness properties. The steam force is directly related to the diameter of the pores. In a smaller diameter pore, the larger pressure on the pores results in larger forces, the steam tends to move to the top surface of the molten pool to escape and overcome the hydrostatic pressure as well as the surface tension, thus the keyhole is formed. Furtherly, this leads to the lack of fusion and the creation of large pores, even the cracks, thereby lowering the mechanical properties [5]. The morphology of the melt pool and grain structure are significantly affected Under different VED. A higher VED results in a deeper and wider melt pool, while a lower VED leads to a shallower and narrower one. The flow and spread of the powder also depend on VED. Differences in crystallization rates influence the distribution of TiC at grain boundaries, which directly relates to the material's mechanical and thermal properties. In summary, as stated above, the quality of an as-printed sample has a close relationship with the processing parameters, and research on optimizing the processing parameters and obtaining the correlations with microstructural data will gain a comprehensive understanding of material properties during the L-PBF process.

In this work, it can be concluded that cracks can be effectively suppressed by adding nano-ceramic particles. There are two main mechanisms for crack formation: liquefaction of low-melting phases and structural liquefaction [50,51]. Carbides in the heat-affected zone have been considered as the primary phase which causes the structural liquefaction [52]. During the L-PBF, the thermal cycling of carbides can be very intense. However, due to the large temperature gradient and fast cooling rate, carbides do not have enough time to dissolve into the surrounding matrix. It has been clarified in previous studies that even introducing the higher carbon content, no liquid film was found at the interface between the carbide and the matrix by the characterization, namely no cracks caused by the structural liquefaction were observed. Similar findings were found in these studies [50,51], which the tendency of structural liquefaction is a strong function of the carbide size. In this study, the TiC particles are the size of 50 nm, therefore, by the addition of the nano-TiC particles will benefit to mitigate the liquefaction effect and reduce the cracks.

4. Conclusion

This paper proposes a method of adding 2 wt% nano- TiC particles to fabricate the IN738LC via L-PBF and the crack-free samples were achieved. The relationship between the processing parameters and the quality of as-printed samples was studied. Based on the nano-TiC strengthening principle, combined with the results from fracture morphology and mechanical tests, the mechanisms of obtaining high-quality TiC-IN738LC were theoretically described. The main conclusions of this study can be summarized as follows:

- (1). The effects of process parameters on the density, porosity, hardness and tensile strength of nano-TiC reinforced IN738LC were comprehensively examined, and by optimizing the parameters, high-strength TiC-IN738LC could be prepared.
- (2). The optimal parameters of high-density and low-porosity L-PBFed TiC-IN738LC are laser energy 225W, scanning speed 750 mm/s, hatch spacing 0.09 mm, and powder layer thickness 0.03 mm.
- (3). By adding TiC nanoparticle to IN738LC, a low-porosity and highstrength TiC-IN738LC was fabricated; Compared with the L-PBFed IN738LC, the microhardness of TiC-IN738LC increased by 20%–40 %, and the tensile strength of TiC-IN738LC improved by 10%–30 %. The synergistic effect of fine grain strengthening mechanism, load-bearing strengthening mechanism and Orowan strengthening mechanism was accounted for the performance enhancement.
- (4). The results in this work provide an experimental reference for the L-PBF parameters of TiC-IN738LC, and furtherly expand the

applications in terms of metal matrix composite in the fields of aerospace and deep-ocean exploration.

Declaration of competing interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Acknowledgements

This work was supported by the National Natural Science Foundation of China [Grant number 51975301], Natural Science Foundation of Zhejiang, China [Grant number LZ22E050002] and the University of Birmingham that provided the funding.

References

- [1] Sanchez S, Smith P, Xu Z, Gaspard G, Hyde CJ, Wits WW, et al. Powder Bed Fusion of nickel-based superalloys: a review. Int J Mach Tool Manufact 2021:165. https:// doi.org/10.1016/j.ijmachtools.2021.103729.
- [2] Shi J, Wang Y. Development of metal matrix composites by laser-assisted additive manufacturing technologies: a review. J Mater Sci 2020;55(23):9883–917. https:// doi.org/10.1007/s10853-020-04730-3.
- [3] Han Q, Gu Y, Gu H, Yin Y, Song J, Zhang Z, et al. Laser powder bed fusion of WCreinforced Hastelloy-X composite: microstructure and mechanical properties. J Mater Sci 2020;56(2):1768–82. https://doi.org/10.1007/s10853-020-05327-6.
- [4] Chen L, Sun Y, Li L, Ren X. Microstructure evolution, mechanical properties, and strengthening mechanism of TiC reinforced Inconel 625 nanocomposites fabricated by selective laser melting. Mater Sci Eng, A 2020:792. https://doi.org/10.1016/j. msea.2020.139655.
- [5] Khorasani A, Gibson I, Awan US, Ghaderi A. The effect of SLM process parameters on density, hardness, tensile strength and surface quality of Ti-6Al-4V. Addit Manuf 2019;25:176–86. https://doi.org/10.1016/j.addma.2018.09.002.
- [6] Tucho WM, Lysne VH, Austbø H, Sjolyst-Kverneland A, Hansen V. Investigation of effects of process parameters on microstructure and hardness of SLM manufactured SS316L. J Alloys Compd 2018;740:910–25. https://doi.org/10.1016/j. jallcom.2018.01.098.
- [7] Kasperovich G, Haubrich J, Gussone J, Requena G. Correlation between porosity and processing parameters in TiAl6V4 produced by selective laser melting. Mater Des 2016;105:160–70. https://doi.org/10.1016/j.matdes.2016.05.070.
- [8] Wang H, Zhang X, Wang GB, Shen J, Zhang GQ, Li YP, et al. Selective laser melting of the hard-to-weld IN738LC superalloy: efforts to mitigate defects and the resultant microstructural and mechanical properties. J Alloys Compd 2019:807. https://doi.org/10.1016/j.jallcom.2019.151662.
- [9] Lv Y, Zhang Z, Zhang Q, Wang R, Sun G, Chen Xi-zhen, et al. Cracking inhibition behavior and the strengthening effect of TiC particles on the CM247LC superalloy prepared by selective laser melting. Mater Sci Eng, A 2022:858. https://doi.org/ 10.1016/j.msea.2022.144119.
- [10] Ogunbiyi O, Jamiru T, Sadiku R, Beneke LW, Adesina O, Adegbola TA. Microstructural characteristics and thermophysical properties of spark plasma sintered Inconel 738LC. Int J Adv Des Manuf Technol 2019;104(1–4):1425–36. https://doi.org/10.1007/s00170-019-03983-w.
- [11] Lemos G, Fredel MC, Pyczak F, Tetzlaff U. Creep resistance improvement of a polycrystalline Ni-based superalloy via TiC particles reinforcement. Mater Sci Eng, A 2022:854. https://doi.org/10.1016/j.msea.2022.143821.
- [12] Wang R, Zhu G, Yang C, Zhou W, Wang D, Dong A, et al. Novel selective laser melting processed in-situ TiC particle-reinforced Ni matrix composite with excellent processability and mechanical properties. Mater Sci Eng, A 2020:797. https://doi.org/10.1016/j.msea.2020.140145.
- [13] Zhou W, Zhu G, Wang R, Yang C, Tian Y, Zhang L, et al. Inhibition of cracking by grain boundary modification in a non-weldable nickel-based superalloy processed by laser powder bed fusion. Mater Sci Eng, A 2020:791. https://doi.org/10.1016/j. msea.2020.139745.
- [14] Gu D, Zhang H, Dai D, Xia M, Hong C, Poprawe R. Laser additive manufacturing of nano-TiC reinforced Ni-based nanocomposites with tailored microstructure and performance. Compos B Eng 2019;163:585–97. https://doi.org/10.1016/j. compositesb.2018.12.146.
- [15] Jia Q, Gu D. Selective laser melting additive manufacturing of TiC/Inconel 718 bulk-form nanocomposites: densification, microstructure, and performance. J Mater Res 2014;29(17):1960–9. https://doi.org/10.1557/imr.2014.130.
- [16] Rong T, Gu D, Shi Q, Cao S, Xia M. Effects of tailored gradient interface on wear properties of WC/Inconel 718 composites using selective laser melting. Surf Coating Technol 2016;307:418–27. https://doi.org/10.1016/j. surfcoat.2016.09.011.
- [17] Zhang B, Bi G, Chew Y, Wang P, Ma G, Liu Y, et al. Comparison of carbon-based reinforcement on laser aided additive manufacturing Inconel 625 composites. Appl Surf Sci 2019;490:522–34. https://doi.org/10.1016/j.apsusc.2019.06.008.
- [18] Zhang B, Bi G, Wang P, Bai J, Chew Y, Nai MS. Microstructure and mechanical properties of Inconel 625/nano-TiB2 composite fabricated by LAAM. Mater Des 2016;111:70–9. https://doi.org/10.1016/j.matdes.2016.08.078.

C. Shu et al.

- [19] Zhang H, Gu D, Ma C, Guo M, Yang J, Zhang H, et al. Understanding tensile and creep properties of WC reinforced nickel-based composites fabricated by selective laser melting. Mater Sci Eng, A 2021:802. https://doi.org/10.1016/j. msea.2020.140431.
- [20] Mishurova T, Artzt K, Haubrich J, Requena G, Bruno G. New aspects about the search for the most relevant parameters optimizing SLM materials. Addit Manuf 2019;25:325–34. https://doi.org/10.1016/j.addma.2018.11.023.
- [21] Koutiri I, Pessard E, Peyre P, Amlou O, De Terris T. Influence of SLM process parameters on the surface finish, porosity rate and fatigue behavior of as-built Inconel 625 parts. J Mater Process Technol 2018;255:536–46. https://doi.org/ 10.1016/j.jmatprotec.2017.12.043.
- [22] Zhang S, Rauniyar S, Shrestha S, Ward A, Chou K. An experimental study of tensile property variability in selective laser melting. J Manuf Process 2019;43:26–35. https://doi.org/10.1016/j.jmapro.2019.03.045.
- [23] Majeed A, Zhang Y, Lv J, Peng T, Atta Z, Ahmed A. Investigation of T4 and T6 heat treatment influences on relative density and porosity of AlSi10Mg alloy components manufactured by SLM. Comput Ind Eng 2020:139. https://doi.org/ 10.1016/j.cie.2019.106194.
- [24] Damon J, Dietrich S, Vollert F, Gibmeier J, Schulze V. Process dependent porosity and the influence of shot peening on porosity morphology regarding selective laser melted AlSi10Mg parts. Addit Manuf 2018;20:77–89. https://doi.org/10.1016/j. addma.2018.01.001.
- [25] Al-Maharma AY, Patil SP, Markert B. Effects of porosity on the mechanical properties of additively manufactured components: a critical review. Mater Res Express 2020;7(12):122001. https://doi.org/10.1088/2053-1591/abcc5d.
- [26] Hu Y, Cong W. A review on laser deposition-additive manufacturing of ceramics and ceramic reinforced metal matrix composites. Ceram Int 2018;44(17): 20599–612. https://doi.org/10.1016/j.ceramint.2018.08.083.
- [27] Webster S, Lin H, Carter III FM, Ehmann K, Cao J. Physical mechanisms in hybrid additive manufacturing: a process design framework. J Mater Process Technol 2021;291:117048. https://doi.org/10.1016/j.jmatprotec.2021.117048.
- [28] Brennan M, Keist J, Palmer T. Defects in metal additive manufacturing processes. J Mater Eng Perform 2021;30(7):4808–18. https://doi.org/10.1007/s11665-021-05919-6.
- [29] Fu J, Li H, Song X, Fu M. Multi-scale defects in powder-based additively manufactured metals and alloys. J Mater Sci Technol 2022. https://doi.org/ 10.1016/j.jmst.2022.02.015.
- [30] Khairallah SA, Anderson AT, Rubenchik A, King WE. Laser powder-bed fusion additive manufacturing: physics of complex melt flow and formation mechanisms of pores, spatter, and denudation zones. Acta Mater 2016;108:36–45. https://doi. org/10.1016/j.actamat.2016.02.014.
- [31] Yusuf S, Chen Y, Boardman R, Yang S, Gao N. Investigation on porosity and microhardness of 316L stainless steel fabricated by selective laser melting. Metals 2017;7(2):64. https://doi.org/10.3390/met7020064.
- [32] Wang X, Carter LN, Pang B, Attallah MM, Loretto MH. Microstructure and yield strength of SLM-fabricated CM247LC Ni-Superalloy. Acta Mater 2017;128:87–95. https://doi.org/10.1016/j.actamat.2017.02.007.
- [33] Bi G, Sun CP, Chen HC, Ng FL. Microstructure and tensile properties of superalloy IN100 fabricated by micro-laser aided additive manufacturing. Mater Des 2014;60: 401–8. https://doi.org/10.1016/j.matdes.2014.04.020.
- [34] Li Y, Liang X, Yu Y, Li H, Kan W, Lin F. Microstructures and mechanical properties evolution of IN939 alloy during electron beam selective melting process. J Alloys Compd 2021;883:160934. https://doi.org/10.1016/j.jallcom.2021.160934.
 [35] Perevoshchikova N, Rigaud J, Sha Y, Heilmaier M, Finnin BC, Labelle E, et al.
- [35] Perevoshchikova N, Rigaud J, Sha Y, Heilmaier M, Finnin BC, Labelle E, et al. Optimisation of selective laser melting parameters for the Ni-based superalloy IN-738 LC using Doehlert's design. Rapid Prototyp J 2017;23(5):881–92. https://doi. org/10.1108/RPJ-04-2016-0063.

- [36] Yu Z, Guo C, Han S, Hu X, Cao L, Xu Z, et al. The effect of Hf on solidification cracking inhibition of IN738LC processed by Selective Laser Melting. Mater Sci Eng, A 2021;804:140733. https://doi.org/10.1016/j.msea.2021.140733.
- [37] Wei S, Wang G, Yu J, Rong Y. Competitive failure analysis on tensile fracture of laser-deposited material for martensitic stainless steel. Mater Des 2017;118:1–10. https://doi.org/10.1016/j.matdes.2017.01.014.
- [38] Yadollahi A, Shamsaei N, Thompson SM, Seely DW. Effects of process time interval and heat treatment on the mechanical and microstructural properties of direct laser deposited 316L stainless steel. Mater Sci Eng, A 2015;644:171–83. https://doi.org/ 10.1016/j.msea.2015.07.056.
- [39] Li P, Zhou J, Li L, Zhang T, Gou Y, Meng X, et al. Tensile fracture behavior of 316L stainless steel components fabricated with hybrid directed energy deposition and thermal milling manufacturing. Appl Phys A 2021;127(3):1–10. https://doi.org/ 10.1007/s00339-021-04381-4.
- [40] Fiocchi J, Tuissi A, Biffi C. Heat treatment of aluminium alloys produced by laser powder bed fusion: a review. Mater Des 2021;204:109651. https://doi.org/ 10.1016/j.matdes.2021.109651.
- [41] Godec M, Malej S, Feizpour D, Donik Č, Balažic M, Klobčar D, et al. Hybrid additive manufacturing of Inconel 718 for future space applications. Mater Char 2021;172: 110842. https://doi.org/10.1016/j.matchar.2020.110842.
- [42] Zhang S, Wei P, Chen Z, Li B, Huang K, Zou Y, et al. Graphene/ZrO2/aluminum alloy composite with enhanced strength and ductility fabricated by laser powder bed fusion. J Alloys Compd 2022;910:164941. https://doi.org/10.1016/j. iallcom.2022.164941.
- [43] Chen Z, Wei P, Zhang S, Lu B, Zhang L, Yang X, et al. Graphene reinforced nickelbased superalloy composites fabricated by additive manufacturing. Mater Sci Eng, A 2020;769:138484. https://doi.org/10.1016/j.msea.2019.138484.
- [44] Hansen N. Hall–Petch relation and boundary strengthening. Scripta Mater 2004;51 (8):801–6. https://doi.org/10.1016/j.scriptamat.2004.06.002.
- [45] El-Awady JA. Unravelling the physics of size-dependent dislocation-mediated plasticity. Nat Commun 2015;6(1):5926. https://doi.org/10.1038/ncomms6926.
- [46] Zhang Z, Xie Y, Huo X, Chan SLI, Liang J, Luo Y, et al. Microstructure and mechanical properties of ultrafine grained CoCrFeNi and CoCrFeNiAl0.3 high entropy alloys reinforced with Cr2O3/Al2O3 nanoparticles. Mater Sci Eng a-Struc Mater Propert Microstruc Process 2021:816. https://doi.org/10.1016/j. msea.2021.141313.
- [47] Coakley J, Lass EA, Ma D, Frost M, Stone HJ, Seidman DN, et al. Lattice parameter misfit evolution during creep of a cobalt-based superalloy single crystal with cuboidal and rafted gamma-prime microstructures. Acta Mater 2017;136:118–25. https://doi.org/10.1016/j.actamat.2017.06.025.
- [48] Khorasani AM, Gibson I, Ghaderi AR. Rheological characterization of process parameters influence on surface quality of Ti-6Al-4V parts manufactured by selective laser melting. Int J Adv Des Manuf Technol 2018;97(9):3761–75. https:// doi.org/10.1007/s00170-018-2168-6.
- [49] Tian Y, Tomus D, Rometsch P, Wu X. Influences of processing parameters on surface roughness of Hastelloy X produced by selective laser melting. Addit Manuf 2017;13:103–12. https://doi.org/10.1016/j.addma.2016.10.010.
- [50] Zhong M, Sun H, Liu W, Zhu X, He J. Boundary liquation and interface cracking characterization in laser deposition of Inconel 738 on directionally solidified Nibased superalloy. Scripta Mater 2005;53(2):159–64. https://doi.org/10.1016/j. scriptamat.2005.03.047.
- [51] Zhou W, Tian Y, Tan Q, Qiao S, Luo H, Zhu G, et al. Effect of carbon content on the microstructure, tensile properties and cracking susceptibility of IN738 superalloy processed by laser powder bed fusion. Addit Manuf 2022;58:103016. https://doi. org/10.1016/j.addma.2022.103016.
- [52] Dye D, Hunziker O, Reed R. Numerical analysis of the weldability of superalloys. Acta Mater 2001;49(4):683–97. https://doi.org/10.1016/S1359-6454(00)00361-X.