

Boron Nitride: Novel ceramic reductant for low-activity waste vitrification.

RIGBY, Jessica, MARCIAL, Jose, POKORNY, Richard, KLOUZEK, Jaroslav, HAN, Kee Sung, WASHTON, Nancy, FERKL, Pavel, HRMA, Pavel, SCRIMSHIRE, Alex <<http://orcid.org/0000-0002-6828-3620>>, BINGHAM, Paul <<http://orcid.org/0000-0001-6017-0798>>, HALL, Mark, EATON, Will and KRUGER, Albert

Available from Sheffield Hallam University Research Archive (SHURA) at:

<https://shura.shu.ac.uk/34246/>

This document is the Accepted Version [AM]

Citation:

RIGBY, Jessica, MARCIAL, Jose, POKORNY, Richard, KLOUZEK, Jaroslav, HAN, Kee Sung, WASHTON, Nancy, FERKL, Pavel, HRMA, Pavel, SCRIMSHIRE, Alex, BINGHAM, Paul, HALL, Mark, EATON, Will and KRUGER, Albert (2024). Boron Nitride: Novel ceramic reductant for low-activity waste vitrification. Journal of the American Ceramic Society: e20192. [Article]

Copyright and re-use policy

See <http://shura.shu.ac.uk/information.html>

Title: Boron Nitride: Novel ceramic reductant for low-activity waste vitrification

Authors: Jessica C. Rigby ^{*a}, José Marcial ^a, Richard Pokorný ^{b c}, Jaroslav Kloužek ^{b c}, Kee Sung Han ^a, Nancy Washton ^a, Pavel Ferkl ^a, Pavel Hřma ^d, Alex Scrimshire ^e, Paul A. Bingham ^e, Mark Hall ^a, Will Eaton ^a, Albert A. Kruger ^f

* corresponding author email: jessica.rigby@pnnl.gov

^a Pacific Northwest National Laboratory, Richland, WA 99354, USA

^b University of Chemistry and Technology Prague, Technická 5/1905, 166 28 Prague 6, Czechia

^c Institute of Rock Structure and Mechanics of the Czech Academy of Sciences, V Holesovickách 41, 182 09 Prague 8, Czechia

^d AttainX, Support Services Contractor to the Office of River Protection, U.S. Department of Energy, Richland, WA, USA

^e Materials and Engineering Research Institute, College of Business, Technology and Engineering, Sheffield Hallam University, City Campus, Howard Street, Sheffield S1 1WB, United Kingdom

^f U.S. Department of Energy, Office of River Protection, Richland, WA 99352, United States

Abstract:

During vitrification of radioactive wastes excessive foaming reduces processing rates within melter by hindering heat transfer from the molten glass pool to the reacting melter feed. Formulations of low-activity waste (LAW) melter feeds, for vitrification at the Waste Treatment and Immobilization plant at the Hanford Site, conventionally include addition of sucrose to mitigate excessive foaming by hastening the denitration process. However, incomplete combustion of sucrose produces organics such as acetonitrile (C₂H₃N) that may exceed bounding limits of downstream effluent treatment facilities. Using boron nitride (BN) as an

alternate reductant to sucrose, in a representative LAW melter feed reduced C_2H_3N production by 90% by preventing the low-temperature sucrose-nitrate reactions. Furthermore, foaming was suppressed due to the higher decomposition temperature of BN than H_3BO_3 meaning a delayed reaction of a large fraction of boron with the transient glass-forming melt until above the foam onset temperature, thus reducing the quantity and viscosity of the connected melt and trapping less gas in the foam layer.

Keywords: Radioactive waste, vitrification, off-gas, redox, alternate reductants

1. Introduction

Sucrose is the baseline reductant for the vitrification of Hanford low-activity waste (LAW) at the Waste Treatment and Immobilization Plant (WTP) ¹⁻⁷. Sucrose addition to the mixture of LAW and glass forming and modifying additives (GFMA) results in a reduction of foaming behavior and higher production rates for a variety of high-nitrate feed simulants ⁸⁻¹². Sucrose reduces the primary foam during feed-to-glass conversion by reacting with nitrates at low temperatures (200-600 °C), so fewer evolved gases are trapped beneath a viscous connecting melt at higher temperatures (>600 °C) ^{9 10}. The nominal molar quantity of sucrose is scaled such that the atomic ratios of organic carbon from the waste organics and sucrose to nitrogen from nitrates and nitrites is equal to 0.75 ^{10 12 15 16}. This C/N ratio was found optimal in the compositional range tested for SO₃ retention, iron redox state (avoiding overreduction of the melt) and sufficient foam reduction ^{10 12 15 16}.

The sucrose/nitrate reaction that aids in reducing the foam volume also produces acetonitrile (C₂H₃N) in the off-gas system ¹⁷⁻¹⁹. Experimental work using research-scale systems, that resemble the direct-feed LAW (DFLAW) flowsheet, has shown that most of the acetonitrile will partition in the evaporator condensate, which is directed to the Hanford Effluent Treatment Facility (ETF) ¹⁹. The acetonitrile concentration in these effluents was determined to be unsuitable for processing in the ETF exceeding waste acceptance criteria ^{20 21}. Since this was reported, costly downstream modifications to the treatment flowsheet have been adopted for treatment of the acetonitrile in the ETF, including a steam stripper ²⁰⁻²². No promising solutions have yet been proposed upstream of the ETF that would allow flexibility in plant operations and provide less-costly options for future operations.

Estimates of acetonitrile present in the primary off-gas system are around 1 g kg⁻¹ of sugar, or 2 g kg⁻¹ of organic carbon equivalent added to the melter feed ¹⁹. Uncertainties remain where high contents of other organics and water are present in the feed ²³. Alternate carbon-based reductants, such as formic acid, have been explored for the WTP and employed at other vitrification plants ^{8 24-27}. Other carbon-based reductants are not immune from causing concerns in the off-gas system, as many carbon-forms will form products of

incomplete combustion in the off-gas system. Furthermore, formic acid recently caused apprehensions over production of flammable levels of hydrogen, propelling exploration of alternatives^{24 28 29}. Ceramic, or other inorganic reductants, as an alternative to organic reductants, would alleviate many of these concerns, removing the source of added carbon for acetonitrile generation.

Boron nitride ceramic powder provides an isostructural and isoelectronic compound to carbon³⁰. h-BN has a melting temperature of around 3000 °C and³¹ in h-BN nanoplatelets, a stable mass has been observed up to 1000 °C and then the oxidation reaction:



proceeds³². To the authors knowledge, BN has not been added to waste feeds as a reductant, nor were we able to identify any literature pertaining to its addition to any glass-forming melt.

This study endeavors to investigate the potential benefits of BN as a reducing agent in a simulated DFLAW feed and initiate the exploration of BN and other ceramic reductants across waste treatment programs and potentially also into the commercial glass manufacturing industry. By studying the foaming properties and gas evolution in a representative DFLAW melter feed with sucrose compared to alternatives batched with varying ratios of BN, the following study will evaluate the effectiveness of BN as a foam reducing agent and in suppression of acetonitrile evolution. By structural investigation of heat-treated feed samples, the work intends to reveal some of the governing chemistry behind differences in foaming and gas evolution and determine the effect on the glass redox state.

2. Materials and Methods

The 241-AP-107 simulated tank waste feed, herein described as AP-107, was batched as described in Table 1. The GFMA's were batched as described in Table 2, where the nominal AP-107 composition, containing sucrose for the purpose of reducing foam, is based on the "AP107WDFL" formulation³³. From this baseline composition, the other compositions were designed where BN was substituted for C in sucrose in an equimolar ratio. For the feeds with BN added, H_3BO_3 was reduced to account for the excess B, to ensure that the final glass composition was consistent. The bounding case for "maximum" amount of boron nitride addition was a feed in which BN entirely replaced the H_3BO_3 added as a GFMA, which resulted in a "BN/N" ratio of 1.75.

For simplicity, the nomenclature used for BN-bearing melter feeds in this study is BNY where Y is the BN/N molar ratio. Feeds with BN/N molar ratios of 1.75, 0.75, 0.50 and 0.25, were formulated. The raw materials for the simulated waste feeds and GFMA's were batched in deionized water and then thoroughly mixed, before drying for at least 24 hours at 105 °C. Once dry, feeds were crushed to a fine powder using a tungsten carbide puck mill.

Table 1. Nominal composition of the AP-107 simulated waste feed³³.

Table 2. Nominal composition of the AP-107 GFMA's for each variation in sucrose and boron nitride content.

For each composition variation the foam volume profile during melting was measured using a feed volume expansion test (FET) as described by Hilliard and Hrma³⁴, and Marcial, et al.³⁵. Approximately 0.9 g of dried feed was pressed into 13 mm diameter pellets under 7 MPa pressure for 3 intervals of 30 s. The pellets were loaded into a furnace with a viewport and heated from room temperature at 10 °C min⁻¹. Images were taken every 10 °C and the FET trial was deemed complete once the pellet had physically melted to a flat pool, between 1000 and 1150 °C. The volume, V , was estimated assuming rotational symmetry around a vertical axis and then normalized to the volume of the final glass melt, by the equation:

$$V_G = (m_{feed}/\rho_{glass}) (1-L_I) \quad (2)$$

where m_{feed} is the mass of the feed added to form the pellet, ρ_{glass} is the density of the glass (estimated to be 2.5 g cm⁻³) and L_I is the loss on ignition. FET experiments were performed in duplicate or triplicate for error analysis.

For evolved gas analysis (EGA), approximately 1 g of each powdered feed was loaded into a silica test tube with a gas inlet and outlet secured to the top and placed in an electric furnace. The feeds were heated to 1150 °C at a rate of 10 °C min⁻¹ while a Hiden Analytical HPR R&D20 EGA monitored the signals of the mass-to-charge (m/z) values, defined in Table S1, evolving from the test tube. Argon carrier gas at a flow rate of 50 mL min⁻¹ created an inert atmosphere to prevent overlap with gas evolving from the feed, particular O₂ and N₂. The measured intensities of the m/z signals were normalized to the intensity of the carrier gas to convert into parts per million (ppm) values. The inert atmosphere could overestimate the total quantity of gases evolved compared to the air atmosphere that the feed would experience in the furnace, however the comparison of the different feeds in a controlled atmosphere is of interest to this study. Background measurements were taken for approximately five minutes for each feed before beginning the temperature ramp, the background gas quantities were subtracted from the collected quantities of gases evolving during heating.

Ten gram samples of each feed were heated to temperatures representative of key stages of foaming based on the FET results, these temperatures were 105, 400, 700, 1000 and 1150 °C. The feeds were quenched in air once they had reached the desired temperature to provide a snapshot of the chemical nature of the feed at that stage of melting. The samples were then milled and analyzed for composition by electron probe microanalysis/wavelength dispersive spectroscopy (EPMA/WDS) and images of phase distribution shown in the supplementary material. Phase identification and quantification were performed by X-ray diffraction (XRD), and analysis of boron speciation by ¹¹B magic angle spinning nuclear magnetic resonance (MAS NMR).

Elemental mapping was performed using a JEOL 8530F EPMA field emission gun electron microscope outfitted with wavelength dispersive spectrometers operated at 15 keV and 50 nA. Heat treated and dried feed powders were prepared for EPMA by mounting in epoxy resin. Following mounting in epoxy, samples were polished using 200, 400, 600, 800, and 1200 grit silicon carbide (SiC) grinding paper with a mineral oil lubricant. A mineral oil lubricant was used instead of water because some species were water soluble. The polished surfaces were cleaned with ethanol. To reduce charging during EPMA, samples were sputter coated with a 2-nm iridium coating. Elemental maps were taken for Na, Ca, Al, Fe, B, N, and Si.

XRD was performed in the range of 5 to 70 ° 2 θ on a Bruker D8 Advance X-ray diffractometer with a Cu K- α X-ray tube. A step size of 0.015 ° 2 θ and dwell time of 1.5 seconds per step was used for these measurements. Prior to measuring, a 5 wt% spike of CeO₂ internal standard was added to each XRD sample before crushing in a tungsten-carbide puck mill. The amorphous fraction was calculated using the internal standard method and Rietveld refinement in Topas software.

The ¹¹B direct polarization experiments were performed using a 20 Tesla wide bore Varian VNMRs spectrometer, operated with a 4.0 mm triple resonance probe in HX mode and tuned to a ¹¹B frequency of 272.631 MHz. Spectral acquisition was performed by collecting 4096 transients using calibrated ¹¹B $\pi/20$ pulses of 0.4 μ s, a 625 kHz sweep width, a spinning speed of 15 kHz, and a 2.0 s recycle delay. The time domain free induction decays were apodized using exponential functions corresponding to 150 Hz of Lorentzian broadening followed by a Fourier transformation. The 0 ppm reference of ¹¹B resonances was defined using BF₃O(CH₂CH₃)₂ and 0.5 M H₃BO₃ as a secondary reference at 19.6 ppm. Ratios of BO₃:BO₄:BN₃ were calculated using resonance line fittings conducted in the Nuts software environment (Acorn NMR, Inc.). The primary uncertainty in the reported values for BO₃:BO₄:BN₃ ratios arises from spectral noise, which is diminished by collecting many transients for each spectrum. The standard deviation in the BO₃:BO₄:BN₃ ratios estimated with a Monte Carlo algorithm in the Mathematica programming environment (Wolfram) using the root-mean-square deviation of a sample of random spectral noise ^{36 37}. For all BO₃:BO₄:BN₃ ratio values reported here, the error is $\pm$ 0.5% or lower.

The ^{57}Fe Mössbauer spectroscopy was employed to determine the iron redox state of the final glasses. Samples heat-treated to 1150 °C were powdered, diluted with graphite, and inserted into the room temperature spectrometer. Decay of a 25 mCi ^{57}Co source in a Rh matrix produced 14.4 keV γ -rays to be absorbed by the sample. The source oscillated at a constant acceleration by a SeeCo W304 drive unit, and the γ -rays detected by a SeeCo 45431 Kr proportional counter operating with 1.745 kV bias voltage applied to the cathode. Spectra of the photons transmitted through the sample were collected over the velocity range $\pm 12 \text{ mm s}^{-1}$ and were calibrated relative to $\alpha\text{-Fe}$ ³⁷. Recoil software was used to fit pseudo-Voigt doublets to the collected spectra, and the iron redox state was determined by the ratio of the peak areas of Fe^{3+} and Fe^{2+} sites, assuming a recoil-free fraction ratio of $f(\text{Fe}^{3+}/\text{Fe}^{2+}) = 1.0$ ³⁹.

3. Results and Discussion

3.1 Slurry properties

A white film rose to the surface of the slurry feed after BN was added, as shown in Figure 1, likely due to the low density of the BN particles. The feed required mixing at 15 min intervals during the first 3 hours of the drying period. Milling then ensured a homogenous distribution of the BN throughout the powdered feed. WTP LAW design involves continuous mixing of the waste feed and GFCs before entry to the melter². Inhomogeneity of the feed slurry would require consideration where continuous stirring of the feed slurry is not a practical option.

Figure 1. Segregation of the BN powder from the rest of the AP-107 BN0.75 mixed slurry feed.

3.2 Foaming and Gas Evolution

A comparison of major evolving gases, CO, NO, O₂, CO₂ and NO₂ and the feed volume expansion with temperature, is shown in Figure 2 for each of the feeds. Maximum feed volume during FETs of AP-107 with no reducing agent is 18x the volume of glass produced ($V/V_G = 18$). The addition of sucrose, Figure 2b, reduced the maximum foam volume by around 18% ($V/V_G = 15$). Replacing all H₃BO₃ with BN (BN1.75), Figure 2c, delayed the foam onset to above 1000 °C and reduced the maximum foam volume by approximately 77%. For BN0.25, BN0.5 and BN0.75 feeds, the maximum foam volume was reduced by approximately 52, 72 and 81%, respectively. Two foaming maxima are distinct in BN0.75, and to a lesser extent in BN0.5 and BN0.25.

The effect of a higher-temperature foaming pattern on the feed processing in electric melters is not clear. This could mean a thinner cold cap with less overall foam, and therefore increased heat transfer to the reacting feed. Alternatively, foam that collapses at higher temperature could restrict heat transfer directly from the melt to the bottom of the cold cap, thus decreasing the melting rate.

Figure 2. Normalized volumetric expansion and evolution of CO, CO₂, N₂, NO, NO₂ and O₂ gases from AP-107 batched (a) without sucrose, and (b) with sucrose at C/N 0.75, (c) and batched with boron nitride equivalent BN/N of 1.75, (d) 0.75, (e) 0.50 and (f) 0.25.

Without sucrose addition, in Figure 2a, the majority of the NO evolution overlaps with the onset of foaming, yielding the high peak foam volume. With sucrose addition, Figure 2b, a substantial fraction of the NO is evolved at temperatures as low as 250 °C, decreasing the gas produced in the temperature interval of foaming.

For BN0.75, 0.50 and 0.25, in Figures 2d, e and f, the amount of NO and NO₂ evolving between 600-800 °C is similar to the feed without sucrose, contributing to the primary foam peak, and suggesting that unlike sucrose, BN does not react chemically with the nitrogen species in the feed. The quantity of gases in the primary foam region, 700 – 900 °C, is greater in the BN-containing feeds than the nominal and no sucrose AP-107 feeds, but the foam volume is less. The mechanism of foam reduction using sucrose as a reductant is chemical, involving the partial destruction of nitrates at low temperatures, prior to the foam onset ⁴⁰. Whereas, these results suggest, that foam reduction using BN is related to the quantity and/or viscosity of the transient melt forming around the gasses and trapping them as foam. This reasoning is explored in the following section on structure of the material with temperature ^{35 41-43}.

The secondary peak in the BN-containing feeds may be caused by the small N₂ evolution above 900 °C with lesser contribution from SO₃ evolution, Figure 3a. N₂ evolution above 1000 °C is in keeping with the decomposition of BN with temperature from reaction (1) discussed in section 1 ³². The temperature onset of SO₂ evolution decreases with increasing BN content. The amount of SO₃ released is significantly greater in the BN0.75 feed than the other BN containing feeds, while nominal AP-107 does not evolve SO₂ in the temperature region measured. The retention of SO₃ in the glass will be of interest to waste processing and therefore should be investigated further.

With removal of sucrose, and replacement with boron nitride, there is a reduction of over 90% of the acetonitrile produced by the feed during melting, shown in Figure 3b.

Figure 3. (a) SO₂ and (b) acetonitrile evolution nominal AP-107 BN at equivalent BN0.25, 0.50, 0.75 and 1.75.

3.3. Structure and phase composition

For heat-treated AP-107, BN0.25, BN0.50 and BN0.75 at 105, 400, 700, 1000 and 1150 °C proportions of crystalline phases were determined by refinement of collected XRD patterns, given in the supplementary materials, these allowed for quantification of the amorphous phase at each of the temperatures shown in Figure 4.

Figure 4. Mass fraction of crystalline phases in the feed at 105, 400, 700, 1000 and 1150 °C for AP-107 with sucrose and with varying BN content by refinement of XRD patterns and fraction of amorphous phase in the feeds with sucrose and BN at 105, 400, 700, 1000 and 1150 °C.

Figure 4e takes the quantity of crystalline phase and mass loss during melting to approximate the proportion of amorphous phase at each temperature. The difference in the quantity of amorphous phase is significant at 700 °C, where a higher proportion of silica has dissolved into the transient melt in AP-107 than in any of the BN feeds. This would mean the transient melt forming around the other constituents and trapping gases from gas evolving reactions would be much more viscous in the AP-107 feed than the BN-added feeds.

The evolution of the structure of boron, investigated by ¹¹B NMR, is displayed in Figure 5. BN can be ascribed to a signal centered near 26 ppm consistent with previously published chemical shifts for BN₃ ⁴⁴ ⁴⁵. Additional signals observed correspond to BO₃ (~15 ppm) and BO₄ (~0 ppm) consistent with previously published chemical shifts with aluminosilicate glasses ³⁶ ⁴⁶. The doublet observed for BN₃ and BO₃ signals is not due to multiple crystallographic special sites but instead to the quadrupolar line splitting ⁴⁴.

The nominal AP-107 feed, shown in Figure 5a, follows a transition from sharp to broadened features with increasing temperature, without a chemical shift indicating a transition from highly structured crystalline to amorphous BO_3 and BO_4 . The relative abundance of BO_3 increases with temperature, Figure 6. For BN0.75, there is a non-linear relative increase in BN_3 phase proportion from 105 °C to 700 °C. The BO_4 signal is consistent throughout the temperature range, and the proportion of BO_3 changes relatively with the proportion of BN_3 . At 1150 °C, there is no discernable BN and instead BN has oxidized to either BO_3 or BO_4 .

Figure 5. Evolution of boron structure with temperature by ^{11}B NMR of (a) the AP-107 feed, (b) the BN0.75 feed, (c) an AP-107 feed batched with isotopic ^{10}B H_3BO_3 aiming to isolate the BN behavior with temperature and (d) the BN1.75 feed.

The ^{10}B isotopic enrichment, using $\text{H}_3^{10}\text{BO}_3$ -containing BN0.75 melter feed, was performed to directly observe only the evolution of the arrangement of boron from BN during heating. In the ^{10}B enriched feed, Figure 5c, BN remains undissolved until 1000 °C after which, the B oxidizes primarily to BO_3 at 1000 °C while minor quantities of BO_4 emerge at 1150 °C. ^{11}B NMR data of AP-107 1.75BN, where BN is the only boron raw material, in Figure 5d, suggests that BN begins dissolving as temperatures approach 1000 °C. The data mirrors that of the ^{10}B -enriched feed, apart from there being a greater relative proportion of BO_4 structural units.

Figure 6. Proportion of ^{11}B as BN_3 , BO_3 and BO_4 structures by ^{11}B NMR for the (a) the nominal AP-107 feed (b) the BN0.75 feed, (c) a BN0.75 feed batched with isotopic ^{10}B H_3BO_3 aiming to isolate the BN behavior with temperature and (d) the BN1.75 feed.

The decomposition of BN observed by ^{11}B NMR, Figure 6, shows no interaction of BN with other feed components until above the foam onset temperature found in the feed expansion curve in Figure 2 to be >700 °C. With boron being a key component of the low-temperature transient glass forming melt in AP-107, this is the origin of the lack of amorphous phase fraction in the BN-containing feeds. Since both less

silica and boron are dissolved into the transient melt, the melt readily collapses causing lower overall foam volume despite large quantities of gases evolving. Both the quantity and viscosity of transient melt are reduced compared to the nominal feed containing sucrose at 700 °C where the major gas evolution occurs.

Once the boron from BN starts to react with the transient melt, the rate of silica dissolution increases in the BN0.25, 0.50 and 0.75, Figure 4, such that they match the fraction in the nominal AP-107 feed by 1000 °C. This will increase the viscosity of the glass-forming melt and begin trapping more gases, causing the secondary foam peak observed, predominantly in the higher BN feeds, Figure 2. The oxidation reaction (1) of BN postulated to explain the N₂ gas evolution peak >1000 °C in section 3.2, from the literature in section 1, is also supported by the BN decomposition in Figures 5 and 6.

3.4 Iron Redox

Hyperfine fitting parameters of the pseudo-Voigt functions fitted to the ⁵⁷Fe Mössbauer data in Figure 7 are detailed in Table 3 along with the iron redox state of each sample based on the relative intensities of the Fe³⁺ and Fe²⁺ features identified from the spectra ⁴⁷.

Figure 7. χ -VBF of the ⁵⁷Fe Mössbauer spectra of (a) the nominal AP-107 1150 °C sample, (b) the BN0.25 1150 °C sample, (c) the BN0.50 1150 °C sample and (d) the BN0.75 1150 °C sample.

For the nominal AP-107 feed only a single Fe³⁺ doublet is resolved. With increasing BN content, the proportion of iron in Fe²⁺ sites increases, beginning at an abundance of 24 ± 2 % in the BN0.25 sample and reaching 55 ± 2 % for the BN0.75 sample making the redox state of Fe in the BN0.75 sample (Fe³⁺/Fe_T) approximately 0.45. Where Fe²⁺ phases are present, only one Fe³⁺ site is resolvable. In all three samples, the Fe³⁺ site is tetrahedral on average. There are no magnetic phases resolved in either of the spectra ⁴⁸.

Table 3. Hyperfine splitting parameters from pseudo-Voigt fits of ⁵⁷Fe Mössbauer spectra collected for AP-107 and BN0.75 glasses. CS relative to α -Fe, ± 0.02 mm s⁻¹ relative abundance ± 2 %.

The reduction of iron from Fe^{3+} to Fe^{2+} correlates with the BN content. Over reducing the melt can lead to undesirable phenomena, such as the precipitation of metallic phases and sulfides ^{26 49}. $\text{Fe}^{2+}/\text{Fe}^{3+}$ ratios between 0.09 and 0.33 are suggested for processing of nuclear waste to “provide sufficient safety against foaming or precipitation” ^{49 50}. The heavily reduced iron in the BN-containing feeds exposes the insufficiency in assuming an equivalent reducing power between BN and the C in sucrose. Perhaps the use of a more robust stoichiometric calculation for BN addition would be suitable for implementation in this case ²³. Additional discussion on this is provided in the supplementary materials.

4. Conclusion

Employing BN as a replacement for sucrose as an alternate reductant in the LAW waste feed studied reduced 90% of the acetonitrile produced during melting. If implemented in the WTP, this could alleviate strain on secondary liquid effluent waste processing.

In replacing the sucrose, a proportion of the glass forming additive H_3BO_3 was also removed to account for the B in BN. The higher-temperature incorporation of boron in the transient glass-forming melt caused by this replacement is the mechanism that leads to a reduction in foaming. Representative melter testing and observation of the cold cap would be required to understand how such foaming behavior influences the processing rates of the feeds in a melter. Based on the mechanism of foam control, similar results could be achieved with other ceramic compounds with decomposition temperatures high enough to withhold glass forming species from the low-temperature transient melt, such as B_4C , SiC , B_6Si .

While a comprehensive study of all impacts of a change of reductant to the waste treatment and immobilization plant processing flowsheet and glass product quality is beyond the scope of the present paper, demonstration of foam control and redox manipulation using ceramic compounds provides potential avenues for exploration that could enhance operational flexibility at the waste treatment and immobilization plant as well as other glass melting processes, and further optimizing the BN addition, e.g. adding less than $\text{BN/N} = 0.25$, for desired glass properties while examining whether foam control is still achieved.

5. Acknowledgments:

The authors gratefully acknowledge financial support from the U.S. Department of Energy (DOE) Waste Treatment and Immobilization Plant Project. Pacific Northwest National Laboratory is operated by Battelle for DOE under contract DE-SAC05-76RL01830. A portion of the research was performed using the Mössbauer capabilities at the Materials Engineering and Research Institute at Sheffield Hallam University. Richard Pokorny acknowledges the financial support from the Czech Ministry of Education, Youth and Sports Project No. LUAUS23062.

6. References

1. Larson, D. E., Watrous, R. A., Kruger, O. L., Nelson, J. L., Fort, L. A., Bates, S. O., Schmidt, A. J., Peterson, M. E., Nakaoka, R. K., Perez, J. M., Sevigny, G. J., Goles, R. W., Elmore, M. R., Scheele, R. D., Barnes, S. M., Brouns, R. A., Scott, J. L., Flour Technology. (1996) Hanford Waste Vitrification Plant Technical Manual. Pacific Northwest National Laboratory.
2. Kim, D. S., Kruger, A. A., Vienna, J. D. (2012) Preliminary ILAW Formulation Algorithm Description, 24590 LAW RPT-RT-04-0003, Rev. 1. Office of River Protection.
3. Matlack, K. S., Muller, I. S., Callow, R. A., D'Angelo, N., Bardekci, T., Joseph, I., Pegg, I. L. (2011) Improving Technetium Retention in Hanford LAW Glass – Phase 2. (VSL-11R2260-1) Vitreous State Laboratory. Catholic University of America.
4. Darling, D. B., Lee, K. P., Swanberg, D. J., Cree, L. H. Department of Energy Responses to the Nuclear Regulatory Commission Request for Additional Information on the Draft Waste Incidental to Reprocessing Evaluation for Vitrification of Low Activity Waste. Office of River Protection.
5. Goel, A., McCloy, J. S., Pokorny, R., & Kruger, A. A. (2019). Challenges with vitrification of Hanford High-Level Waste (HLW) to borosilicate glass – An overview. *Journal of Non-Crystalline Solids: X*, 4, 100033. <https://doi.org/10.1016/j.nocx.2019.100033>
6. Marcial, J., Riley, B. J., Kruger, A. A., Lonergan, C. E., & Vienna, J. D. (2023). Hanford Low-Activity Waste Vitrification: A Review. *Journal of Hazardous Materials*, 461. <https://doi.org/10.1016/j.jhazmat.2023.132437>
7. Vienna, J. D. (2010). Nuclear Waste Vitrification in the United States: Recent Developments and Future Options: Nuclear Waste Vitrification in the United States. *International Journal of Applied Glass Science*, 1(3), 309–321. <https://doi.org/10.1111/j.2041-1294.2010.00023.x>

8. Bickford, D. F., Hrma, P., & Bowan, B. W. (1990). Control of Radioactive Waste Glass Melters: II, Residence Time and Melt Rate Limitations. *Journal of the American Ceramic Society*, 73(10), 2903–2915. <https://doi.org/10.1111/j.1151-2916.1990.tb06693.x>
9. Bunnell, L. R. (1988). Laboratory work in support of West Valley glass development (PNL-6539; Nuclear Waste Treatment Program). Pacific Northwest National Laboratory. <https://doi.org/10.2172/5196678>
10. Matlack, K. S., Gong, W., Muller, I. S., Joseph, I. & Pegg, I. L. (2005). Final Report—LAW Envelope C Glass Formulation Testing to Increase Waste Loading, VSL-05R5900-1 (ORP-56323 Rev 0, 1109496). Vitreous State Laboratory, The Catholic University of America. <https://doi.org/10.2172/1109496>
11. Matlack, K. S., Muller, I. S., Gong, W. & Pegg, I. L. (2006). Final Report—DuraMelter 100 Tests to Support LAW Glass Formulation Correlation Development, VSL-06R6480-1, Rev. 0 (ORP-56324/VSL-06R6480-1). Vitreous State Laboratory, The Catholic University of America. <https://doi.org/10.2172/1109494>
12. Matlack, K. S., Perez-Cardenas, F., Pegg, I. L., Macedo, P. B., Buechele, A. C., Hojaji, H., Muller, I. S., & Morgan, S. P. (2001). Melter Tests with LAW Envelope A and C Simulants to Support Enhanced Sulfate Incorporation (ORP-63503/VSL-01R3501-2). Vitreous State Laboratory, The Catholic University of America.
13. Hrma, P., Schweiger, M. J., Humrickhouse, C. J., Moody, J. A., Tate, R. M., Rainsdon, T. T., Tegrotenhuis, N. E., Arrigoni, B. M., Marcial, J., Rodriguez, C. P., & Tincher, B. H. (2010). Effect of Glass-batch Makeup on the Melting Process. *Ceramics-Silikaty*, 54(3), 193–211.
14. Lee, S., Jin, T., Rivers, E., Kloužek, J., Luksic, S., Marcial, J., George, J., Dixon, D. R., Eaton, W. C., & Kruger, A. A. (2022). Effect of sucrose on technetium and rhenium retention during vitrification of low-activity wastes. *Journal of the American Ceramic Society*, 105(12), 7321–7333. <https://doi.org/10.1111/jace.18701>

15. Matlack, K. S., McKeown, D., Hojaji, H., Muller, I. S., Morgan, S. P., Buechele, A. C., Perez-Cardenas, F., Pegg, I. L., & Macedo, P. B. (2000). Melter Tests with LAW Envelope B Simulants to Support Enhanced Sulfate Incorporation (ORP-63502/VSL-00R3501-1). Vitreous State Laboratory, The Catholic University of America.
16. Matlack, K. S., Pegg, I. L., & Gong, W. (2003). Final Report: Compositional Variation Tests on DuraMelter 100 with LAW Sub-Envelope A3 Feed in Support of the LAW Pilot Melter (ORP-63485/VSL-01R62N0-1 Rev. 2). Vitreous State Laboratory, The Catholic University of America.
17. Matlack, K., & Pegg, I. (2017). Compilation of Off-Gas Vapor and Liquid Phase Organic Information from Scale Melter Testing of LAW Simulants (VSL-17S4450-1, Rev A) (ORP-67602-00/VSL-17L4450-1). Vitreous State Laboratory, The Catholic University of America. <https://doi.org/10.2172/1845414>
18. Matlack, K. S., Muller, I. S., Abramowitz, H., Joseph, I., & Pegg, I. L. (2017). Support for DF LAW Flowsheet Development (ORP-61653/VSL-17R4250-1). Vitreous State Laboratory, The Catholic University of America.
19. Matlack, K., & Pegg, I. (2019). Estimates of Acetonitrile Generation from Scale Melter Testing of LAW Simulants (VSL-19S4573-1, Rev A) (ORP-67600-00/VSL-19S4573-1). Vitreous State Laboratory, The Catholic University of America. <https://doi.org/10.2172/1844981>
20. Veach, K. J. (2022) ETF Acetonitrile Steam Stripper Process Control Narrative. Sargent & Lundy for Washington River Protection Solutions, LLC. RRP-RPT-62622.
21. Parsons. (2023). Waste Treatment and Immobilization Plant High-Level Waste Treatment Analysis of Alternatives (DE-NA0002895; Enterprise Construction Management Services). Office of River Protection.
22. Pegg, I. L., Mecholsky, N., Brandys, M., & Skeen, R. S. (2020). Acetonitrile Destruction in ETF Feed Solutions by UV/OX and Persulfate (WRPS-66058/VSL-20R4850-1). Washington River Protection Solutions.

23. Kunc, J., Kloužek, J., Vernerová, M., Cincibusová, P., Ferkl, P., Hall, M. A., Eaton, W. C., Hrma, P., Guillen, D. P., Kruger, A. A., & Pokorný, R. (2023). Effect of Feed Composition on the Production of Off-Gases during Vitrification of Simulated Low-Activity Nuclear Waste. *Progress in Nuclear Energy*, 166(104932). <https://doi.org/10.1016/j.pnucene.2023.104932>
24. Lambert, D. P., Pickenheim, B. R., Stone, M. E., Newell, J. D., & Best, D. R. (2011). Glycolic-Formic Acid Flowsheet Final Report for Downselection Decision (SRNL-STI-2010-00523, 1013045). Savannah River National Laboratory. <https://doi.org/10.2172/1013045>
25. Larson, D. E. (1996). Hanford High-Level Waste Vitrification Program at the Pacific Northwest National Laboratory: Technology development—Annotated bibliography (PNNL-10955). Pacific Northwest National Laboratory. <https://doi.org/10.2172/394919>
26. Smith, P. A., Vienna, J. D., & Merz, M. D. (1995). NCAW feed chemistry: Effect of starting chemistry on melter offgas and iron redox (PNL-10517). Pacific Northwest National Laboratory. <https://doi.org/10.2172/211347>
27. Rigby, J. C., Dixon, D. R., Kloužek, J., Pokorný, R., Thompson, P. B. J., Scrimshire, A., Kruger, A. A., Bell, A. M. T., & Bingham, P. A. (2023). Alternative reductants for foam control during vitrification of high-iron High Level Waste (HLW) feeds. *Journal of Non-Crystalline Solids*, 608, 122240. <https://doi.org/10.1016/j.jnoncrysol.2023.122240>
28. Choi, A. S. (2011). Melter Off-Gas Flammability Assessment for DWPF Alternate Reductant Flowsheet Options (SRNL-STI-2011-00321; p. SRNL-STI-2011-00321, 1019027). Savannah River National Laboratory. <https://doi.org/10.2172/1019027>
29. Choi, A. (2014). DWPF Melter Off-Gas Flammability Model for the Nitric-Glycolic Acid Flowsheet (SRNL-STI-2014-00355). Savannah River National Laboratory. <https://doi.org/10.2172/1154717>
30. Han, W.-Q. (2008). Anisotropic Hexagonal Boron Nitride Nanomaterials: Synthesis and Applications (BNL-81439-2008-BC; Multi Metallic and Metal Oxide Nanomaterials for Life Sciences, pp. 1–60). Center for Functional Nanomaterials, Brookhaven National Laboratory. <https://doi.org/10.1002/9783527610419.ntls0161>

31. Solozhenko, V. L., Turkevich, V. Z., & Holzapfel, W. B. (1999). Refined Phase Diagram of Boron Nitride. *The Journal of Physical Chemistry B*, 103(15), 2903–2905. <https://doi.org/10.1021/jp984682c>
32. Kostoglou, N., Polychronopoulou, K., & Rebholz, C. (2015). Thermal and chemical stability of hexagonal boron nitride (h-BN) nanoplatelets. *Vacuum*, 112, 42–45. <https://doi.org/10.1016/j.vacuum.2014.11.009>
33. Matlack, K. S., Abramowitz, H., Muller, I. S., Joseph, I., & Pegg, I. L. (2018). DFLAW Glass and Feed Qualifications for AP-107 to Support WTP Start-Up and Flow-Sheet Development (VSL-18R4500-1). Vitreous State Laboratory, The Catholic University of America.
34. Hilliard, Z., & Hřma, P. (2016). A Method for Determining Bulk Density, Material Density, and Porosity of Melter Feed During Nuclear Waste Vitrification. *Journal of the American Ceramic Society*, 99(1), 98–105. <https://doi.org/10.1111/jace.13919>
35. Marcial, J., Luksic, S., Kloužek, J., Vernerová, M., Cutforth, D., Varga, T., Hřma, P., Kruger, A., & Pokorný, R. (2022). In-situ X-ray and visual observation of foam morphology and behavior at the batch-melt interface during melting of simulated waste glass. *Ceramics International*, 48(6), 7975–7985. <https://doi.org/10.1016/j.ceramint.2021.11.344>
36. McCloy, J., Washton, N., Gassman, P., Marcial, J., Weaver, J., & Kukkadapu, R. (2015). Nepheline crystallization in boron-rich alumino-silicate glasses as investigated by multi-nuclear NMR, Raman, & Mössbauer spectroscopies. *Journal of Non-Crystalline Solids*, 409, 149–165. <https://doi.org/10.1016/j.jnoncrysol.2014.11.013>
37. Sutovich, K. J., Peters, A. W., Rakiewicz, E. F., Wormsbecher, R. F., Mattingly, S. M., & Mueller, K. T. (1999). Simultaneous Quantification of Brønsted- and Lewis-Acid Sites in a USY Zeolite. *Journal of Catalysis*, 183(1), 155–158. <https://doi.org/10.1006/jcat.1998.2379>
38. Page, J. E., Topping, C. V., Scrimshire, A., Bingham, P. A., Blundell, S. J., & Hayward, M. A. (2018). Doped Sr₂FeIrO₆—Phase Separation and a $J_{\text{eff}} \neq 0$ State for Ir⁵⁺. *Inorganic Chemistry*, 57(16), 10303–10311. <https://doi.org/10.1021/acs.inorgchem.8b01539>

39. Ahmadzadeh, M., Scrimshire, A., Mottram, L., Stennett, M. C., Hyatt, N. C., Bingham, P. A., & McCloy, J. S. (2020). Structure of NaFeSiO_4 , $\text{NaFeSi}_2\text{O}_6$, and $\text{NaFeSi}_3\text{O}_8$ glasses and glass-ceramics. *American Mineralogist*, 105(9), 1375–1384. <https://doi.org/10.2138/am-2020-7285>
40. Appel, C. J., Kloužek, J., Jani, N., Lee, S. M., Dixon, D. R., Hrma, P., Pokorný, R., Schweiger, M. J., & Kruger, A. A. (2019). Effect of sucrose on foaming and melting behavior of a low-activity waste melter feed. *Journal of the American Ceramic Society*, 102(12), 7594–7605. <https://doi.org/10.1111/jace.16675>
41. Ferkl, P., Hrma, P., Abboud, A. W., Guillen, D. P., Vernerov, M., Kloužek, J., Hall, M., Kruger, A. Pokorný, R. (2023) Conversion degree and heat transfer in the cold cap and their effect on glass production rate in an electric melter. *International Journal of Applied Glass Science*, 14, 318–329.
42. Khawand, J., Kloužek, J., Vernerová, M., Cincibusová, P., Hrma, P., Kruger, A. A., & Pokorný, R. (2023). Effect of sucrose on the oxidation-reduction conditions and retention of rhenium during vitrification of low-activity waste. *Journal of Nuclear Materials*, 573, 154155. <https://doi.org/10.1016/j.jnucmat.2022.154155>
43. Marcial, J., Pokorný, R., Kloužek, J., Vernerová, M., Lee, S., Hrma, P., & Kruger, A. A. (2020). Effect of water vapor and thermal history on nuclear waste feed conversion to glass. *International Journal of Applied Glass Science*, 12, 145–157.
44. Gervais, C., Maquet, J., Babonneau, F., Duriez, C., Framery, E., Vaultier, M., Florian, P., & Massiot, D. (2001). Chemically Derived BN Ceramics: Extensive ^{11}B and ^{15}N Solid-State NMR Study of a Preceramic Polyborazilene. *Chemistry of Materials*, 13(5), 1700–1707. <https://doi.org/10.1021/cm001244l>
45. Love, A. M., Thomas, B., Specht, S. E., Hanrahan, M. P., Venegas, J. M., Burt, S. P., Grant, J. T., Cendejas, M. C., McDermott, W. P., Rossini, A. J., & Hermans, I. (2019). Probing the Transformation of Boron Nitride Catalysts under Oxidative Dehydrogenation Conditions. *Journal of the American Chemical Society*, 141(1), 182–190. <https://doi.org/10.1021/jacs.8b08165>

46. Marcial, J., Saleh, M., Watson, D., Martin, S. W., Crawford, C. L., & McCloy, J. S. (2019). Boron-speciation and aluminosilicate crystallization in alkali boroaluminosilicate glasses along the $\text{NaAl}_{1-x}\text{B}_x\text{SiO}_4$ and $\text{LiAl}_{1-x}\text{B}_x\text{SiO}_4$ joins. *Journal of Non-Crystalline Solids*, 506, 58–67. <https://doi.org/10.1016/j.jnoncrysol.2019.01.001>
47. Darby Dyar, M. (1985). A review of Mössbauer data on inorganic glasses: The effects of composition on iron valency and coordination. *American Mineralogist*, 70(3–4).
48. Oh, S. J., Cook, D. C., & Townsend, H. E. (1998). Characterization of iron oxides commonly formed as corrosion products on steel. *Hyperfine Interactions*, 112, 59–66.
49. Reigel, M. M. (2015) Literature Review: Assessment of DWPF Melter and Melter Off-gas System Lifetime. Savannah River National Laboratory. SRNL-STI-2014-00134
50. Schreiber, H. D. & Hockman, A. L. (1987) Redox Chemistry in Candidate Glasses for Nuclear Waste Immobilization. *Journal of the American Ceramic Society*, 70(8), 591-94.

List of Figures

Figure 1. Segregation of the BN powder from the rest of the AP-107 BN0.75 mixed slurry feed.

Figure 2. Normalized volumetric expansion and evolution of CO, CO₂, N₂, NO, NO₂ and O₂ gases from AP-107 batched (a) without sucrose, and (b) with sucrose at C/N 0.75, (c) and batched with boron nitride equivalent BN/N of 1.75, (d) 0.75, (e) 0.50 and (f) 0.25.

Figure 3. (a) SO₂ and (b) acetonitrile evolution nominal AP-107 BN at equivalent BN0.25, 0.50, 0.75 and 1.75.

Figure 4. Mass fraction of crystalline phases in the feed at 105, 400, 700, 1000 and 1150 °C for AP-107 with sucrose and with varying BN content by refinement of XRD patterns and fraction of amorphous phase in the feeds with sucrose and BN at 105, 400, 700, 1000 and 1150 °C.

Figure 5. Evolution of boron structure with temperature by ¹¹B NMR of (a) the AP-107 feed, (b) the BN0.75 feed, (c) an AP-107 feed batched with isotopic ¹⁰B H₃BO₃ aiming to isolate the BN behavior with temperature and (d) the BN1.75 feed.

Figure 6. Proportion of ¹¹B as BN₃, BO₃ and BO₄ structures by ¹¹B NMR for the (a) the nominal AP-107 feed (b) the BN0.75 feed, (c) a BN0.75 feed batched with isotopic ¹⁰B H₃BO₃ aiming to isolate the BN behavior with temperature and (d) the BN1.75 feed.

Figure 7. χ -VBF of the ⁵⁷Fe Mössbauer spectra of (a) the nominal AP-107 1150 °C sample, (b) the BN0.25 1150 °C sample, (c) the BN0.50 1150 °C sample and (d) the BN0.75 1150 °C sample.

List of Tables

Table 1. Nominal composition of the AP-107 simulated waste feed ³³.

Table 2. Nominal composition of the AP-107 GFMA's for each variation in sucrose and boron nitride content.

Table 3. Hyperfine splitting parameters from pseudo-Voigt fits of ⁵⁷Fe Mössbauer spectra collected for AP-107 and BN0.75 glasses. CS relative to α -Fe, $\pm 0.02 \text{ mm s}^{-1}$ relative abundance $\pm 2 \%$.